



VisCalor®

in accordance with DIN EN ISO 4049

Carefully read instructions prior to use

Product description:

VisCalor is a light-curing, radiopaque, nano-hybrid restorative material. VisCalor contains 83% inorganic fillers (by weight) and is used with a dentin enamel bond. VisCalor is preheated prior to application. The temperature increase results in decreased viscosity, thus enabling easy insertion in the cavity as well as very good adaptation of the composite to the cavity walls. After application, the viscosity increases again as the composite cools down. In this state the material is very easy to sculpt.

Shades:

A1, A2, A3, A3.5, GA3.25, A4, B1, B2, OA2, incisal, BL

Indications:

- Class I to V restorations
- Base fill (restoration base) in Class I and II cavities
- Reconstruction of anterior teeth damaged by trauma
- Veneering discolored anterior teeth
- Corrections in shape and shade to improve esthetics
- Interlocking, splinting of loose teeth
- Repairing of veneers, enamel defects, and temporary C&B materials
- Extended fissure sealing
- Restoration of deciduous teeth
- Core build-up
- Composite inlays

Contraindications:

VisCalor contains methacrylate and BHT. VisCalor should therefore not be used in patients with a known hypersensitivity (allergy) to these ingredients.

Patient target group:

VisCalor is suitable for use in all patients without any age or gender restrictions.

Performance features:

The product's performance features satisfy the requirements of its intended use and the relevant product standards.

Use:

User:
VisCalor should only be applied by a professionally trained dental practitioner.

Preparation:

Clean teeth to be treated. If required, mark occlusal contact points. Set a preheating device for composites (e.g. Caps Warmer) to 154.4°F in accordance with the operating instructions. Insert the caps and allow them to warm up (approx. 3 min). Leave in the preheating device for max. one day. Alternatively, the VisCalor Dispenser may be used. To do so, please observe the accompanying instructions for use.

Shade selection:

Clean the teeth before shade selection. The shade is selected in comparison with the tooth while still moist.

Cavity preparation:

In principle, the cavities should be prepared according to the rules for adhesive restorative treatment and preparation should be minimally invasive to conserve healthy dental hard tissue. In the case of treatment of anterior teeth, angle off the enamel margins. Before treatment, clean and dry the cavity. Caries-free cervical lesions do not have to be prepared; thorough cleaning is sufficient here.

Ensure that the work area is sufficiently dry. The use of a rubber dam is recommended.

For cavities with a proximal portion, the use of matrices is recommended. It is helpful to use translucent matrices, wedged in the proximal area. Keeping separation to the minimum makes it easier to shape the proximal contacts and attach a matrix. A suitable pulp-protective liner that can be covered with a stable cement, if necessary, should be applied in close proximity to the pulp.

Bonding material:

VisCalor is applied with a dentin enamel bond, using the adhesive technique. Any light-curing bonding materials may be used. Follow the relevant instructions for use during preparation (etching) and application.

Application:

After warming it in the Caps Warmer, insert the cap into the applicator and apply the material within the next 20 seconds. After 20 seconds, VisCalor will still have a temperature of 141.8°F.

If using the VisCalor Dispenser, use program 1 (149°F). The heating time here is 30 seconds. The material is then kept warm for 2 minutes, 30 seconds. In addition, please observe the instructions for use of the VisCalor Dispenser.

Insert VisCalor directly into the prepared cavity, starting at the lowest point, and fill the cavity from bottom to top. Keep the tip of the caps submerged.

Ensure that the material is applied in a slow and steady flow to prevent air bubbles from forming. Do not apply VisCalor in layers that are more than 2 mm thick; adapt with a suitable instrument and light-cure afterwards.

Light-curing:

Conventional polymerization devices with a wavelength in the range of 400-500 nm are suitable for light-curing the material.

Depending on the light output and chosen shade, the curing times for increments up to 2 mm are:



LED/halogen light	A1, A2, A3, GA3.25, A3.5, A4 B1, B2, incisal, BL	OA2
≥ 1000 mW/cm²	10 s	20 s
≥ 500-1000 mW/cm²	20 s	40 s

Hold the curing light's light-emitting light guide as close to the surface of the restoration as possible; the curing may otherwise be inadequate. Inadequate curing can result in discoloration and lead to complaints.

Finishing:

The restoration can be finished and polished immediately after removing the matrices (e.g. fine or extra-fine diamond bur, polisher). The tooth should be fluoridated as a final step.

VisCalor can be used in accordance with known methods for direct or indirect inlays. The physical stability values are improved even more by the extreme external (additional) curing.

Warnings/precautionary measures:

- Phenolic substances, especially products containing eugenol or thymol, interfere with the curing of filling composites. Thus, avoid the use of zinc oxide eugenol cements or other materials containing eugenol in combination with filling composites.
- Each VisCalor Caps unit should be used for one patient only.
- When using the VisCalor Dispenser, VisCalor Caps should be heated only once.
- Caps should be applied exerting uniform but not excessive pressure.
- After warming, extract VisCalor in a preheating device. High extrusion forces occur in an unwarmed state.
- The device must be allowed to cool down completely (approx. 2-3 minutes) between two uses with the VisCalor Dispenser so as to avoid overheating.
- Our information and/or advice do not relieve you of the obligation of checking that the products supplied by us are suitable for the intended purpose.

Constituents (in descending order according to content):

Barium aluminium borosilicate glass, silica, BisGMA, TCDDMA, initiators, stabilizers, color pigments

Storage:

Store at 39°F to 73°F (4°C to 23°C). Do not use after the expiration date.

Disposal:

Dispose of the product in accordance with local regulations.

Reporting obligation:

Serious events such as death, temporary or permanent serious deterioration of a patient's, user's or other person's condition and a serious risk to public health that arise or could have arisen in association with the use of VisCalor must be reported to VOCO GmbH and the responsible authority.

PRODUCT ORDERING INFORMATION:

Kit Dispenser 80 x 0.25 gm (16 x A1, 32 x A2, 16 x A3, 16 x A3.5),
VisCalor Dispenser REF 6106

Kit Caps Warmer 80 x 0.25 gm (16 x A1, 32 x A2, 16 x A3, 16 x A3.5),
Caps Warmer REF 6107

Kit + Bond Caps 80 x 0.25 gm (16 x A1, 16 x A2, 16 x A3, 16 x GA3.25, 16 x B1), **Futurabond U SingleDose** REF 6108

16 x 0.25 gm in the following shades

A1	REF 6113	A4	REF 6118
A2	REF 6114	B1	REF 6119
A3	REF 6115	B2	REF 6120
GA3.25	REF 6116	Incisal	REF 6121
A3.5	REF 6117	OA2	REF 6122

This material has been developed solely for use in dentistry. Processing should be done strictly according to the instructions for use.

VOCO recognizes its responsibility to replace products if proven to be defective. VOCO does not accept liability for any damage or loss, directly or indirectly, stemming from the use of or inability to use the products described. Before using, it is the responsibility of the user to determine the suitability of the product for its intended use. The user assumes all risk and liability in connection therewith.

Descriptions and data constitute no warranty of attributes and are not binding.

CAUTION: U.S. Federal Laws restrict this device to sale by or on the order of a dentist.

No person is authorized to provide any information which deviates from the information provided in the instructions for use.

For questions or comments, please call 1-888-658-2584.

Keep this material out of reach of children.

For dental use only.

An explanation of the symbols used in labeling can be found at www.voco.dental/symbols

Manufactured by:

VOCO GmbH Phone +49 (4721) 719-0
Anton-Flettner-Str. 1-3 Fax +49 (4721) 719-140
27472 Cuxhaven e-mail: marketing@voco.com
Germany www.voco.dental



VisCalor®

Corresponde a DIN EN ISO 4049

Leer esmeradamente las instrucciones antes del uso

Descripción del producto:

VisCalor es un material de restauración nanohíbrido fotopolimerizable radiopaco. VisCalor contiene un 83 % en peso de relleno inorgánico y se aplica con un adhesivo para dentina-esmalte. VisCalor se calienta antes de su aplicación. El incremento de la temperatura provoca una reducción de la viscosidad y, con ello, permite una fácil inserción en la cavidad y una excelente adaptación del composite a las paredes de la cavidad. Después de la aplicación, la viscosidad vuelve a aumentar a medida que el composite se enfria. En este estado se puede modelar muy bien.

Colores:

A1, A2, A3, A3.5, GA3.25, A4, B1, B2, OA2, incisal, BL

Indicaciones:

- Restauraciones de las clases I a V
- Revestimiento (base de obturación) de cavidades de las clases I y II
- Reconstrucción de dientes frontales dañados por traumatismo
- Revestimiento de dientes frontales descoloridos
- Correcciones de forma y color para una mejor estética
- Inmovilización, ferulización de dientes con fijación insuficiente
- Reparaciones de facetas, reparaciones de defectos en el esmalte y de coronas y puentes provisionales
- Sellado de fisuras ampliado
- Restauraciones de dientes de leche
- Reconstrucciones de muñón
- Inlays de composite

Contraindicaciones:

VisCalor contiene metacrilatos y BHT. En caso de existir hipersensibilidad conocida (alergia) a estas sustancias, absténgase de aplicar VisCalor.

Pacientes destinatarios:

VisCalor puede emplearse en todo tipo de pacientes, sin limitaciones de edad o sexo.

Características:

Las características del producto cumplen los requisitos de la finalidad prevista y las normas de producto pertinentes.

Utilización:

Usuario:

La aplicación de VisCalor debe llevarla a cabo un usuario profesional cualificado y formado en odontología.

Preparación:

Limpie los dientes que vayan a ser tratados. Marque en caso necesario los puntos de contacto oclusales. De acuerdo con las instrucciones, configure un dispositivo de calentamiento para composite (p. ej., Caps Warmer) a una temperatura de 154.4°F. Inserte las cápsulas y deje que se calienten (aprox. 3 min). Déjelas en el dispositivo de calentamiento durante un día como máximo. De forma alternativa puede utilizarse el VisCalor Dispenser.

Consulte para ello las instrucciones de uso adjuntas.

Selección de tonos:

Limpie los dientes antes de determinar el tono. El color se determina en la pieza aún húmeda.

Preparación cavitaria:

En principio, la preparación cavitaria debe realizarse de conformidad con las reglas del tratamiento de obturación adhesivo y de forma mínimamente invasiva para preservar la sustancia dental dura sana. Para restauraciones de dientes anteriores, bisele los bordes del esmalte. Limpie y seque la cavidad antes de su utilización. No es necesario preparar lesiones sin caries en la zona del cuello dental, siendo suficiente realizar una limpieza exhaustiva.

Asegúrese de que el entorno de trabajo está suficientemente seco.

Recomendamos el uso de un dique de goma.

Para aquellas cavidades con parte proximal, se recomienda el uso de auxiliares. Resulta útil asegurar matrices translúcidas en la zona proximal. Una separación mínima facilita el modelado de contacto proximal y la colocación de las matrices.

En zonas cercanas a la pulpa, se ha de colocar una protección adecuada que, de ser necesario, se recubre con una capa de cemento estable.

Material adhesivo:

En la técnica adhesiva, VisCalor se aplica con un adhesivo para dentina-esmalte. Se pueden utilizar todos los materiales de adhesión fotopolimerizables. Observe las respectivas instrucciones de uso en lo que a la preparación (técnica de grabado) y el acabado se refiere.

Aplicación:

Coloque la cápsula calentada en el Caps Warmer en un aplicador y aplique el material antes de que transcurran 20 s. Después de 20 s VisCalor aún tiene una temperatura de 141.8°F. Use el programa 1 (149°F) cuando utilice el VisCalor Dispenser. El tiempo de calentamiento es de 30 s. El material se mantiene caliente durante 2 min y 30 s. Observe también las instrucciones de uso del VisCalor Dispenser. Aplique VisCalor directamente en la cavidad preparada empezando por el punto más profundo y llene la cavidad de abajo a arriba dejando la punta de la cápsula sumergida. Durante la aplicación, asegúrese de que el producto fluya de forma lenta y uniforme para evitar la formación de burbujas de aire.

Aplique VisCalor en capas de no más de 2 mm de grosor, ajuste con un instrumento adecuado y